

Noryl GTX* Resin GTX626

Americas: COMMERCIAL

Blowmolding and extrusion. High heat and chemical resistant.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	83	%	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	95	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	2270	MPa	ASTM D 790
IMPACT	Value	Unit	Standard
Izod Impact, notched, 23°C	336	J/m	ASTM D 256
Izod Impact, notched, -30°C	122	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	31	J	ASTM D 3763
Instrumented Impact Energy @ peak, -30	36	J	ASTM D 3763
THERMAL	Value	Unit	Standard
HDT, 0.45 MPa, 6.4 mm, unannealed	179	°C	ASTM D 648
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL	Value	Unit	Standard
Specific Gravity	1.09	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	1.3 - 1.4	%	SABIC Method
FLAME CHARACTERISTICS	Value	Unit	Standard
UL Recognized, 94HB Flame Class Rating (3)	1.49	mm	UL 94

Source GMD, last updated:01/05/2000

Processing

- Dry for recommended time and temperature as overdrying can cause loss of physical properties and/or create appearance defects.

Parameter	Value	Unit
Extrusion Blow Molding		
Drying Temperature	80	°C
Drying Time	4	hrs
Drying Time (Cumulative)	16	hrs
Melt Temperature (Parison)	275 - 290	°C
Barrel - Zone 1 Temperature	270 - 280	°C
Barrel - Zone 2 Temperature	270 - 280	°C
Barrel - Zone 3 Temperature	270 - 280	°C
Barrel - Zone 4 Temperature	270 - 280	°C
Adapter - Zone 5 Temperature	275 - 290	°C
Head - Zone 6 - Top Temperature	275 - 290	°C
Head - Zone 7 - Bottom Temperature	275 - 290	°C
Mold Temperature	80	°C
Die Temperature	275 - 290	°C

- As screw speed is increased, shear heating increases; reducing barrel temperatures helps keep melt temperature under control.
- Processing temperature must be measured with a hand-held probe as opposed to an internal-head probe.
- A reverse barrel profile may increase output while maintaining the melt temperature.

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Noryl GTX is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company.All rights reserved