

Ultem* Resin SILTEM-STM1500 Europe-Africa-Middle East: COMMERCIAL

SILTEM STM1500 is a flexible siloxane-polyetherimide copolymer for cable and wire coatings. Non-halogenated and

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Taber Abrasion, CS-17, 1 kg	60	mg/1000cy	SABIC Method
Tensile Stress, yield, 50 mm/min	20	MPa	ISO 527
Tensile Stress, break, 50 mm/min	25	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	15	%	ISO 527
Tensile Strain, break, 50 mm/min	110	%	ISO 527
Tensile Modulus, 1 mm/min	590	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	20	MPa	ISO 178
Flexural Stress, break, 2 mm/min	18	MPa	ISO 178
Flexural Modulus, 2 mm/min	470	MPa	ISO 178
IMPACT	Value	Unit	Standard
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	25	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	15	kJ/m ²	ISO 180/1A
THERMAL	Value	Unit	Standard
CTE, 23°C to 80°C, flow	1.1E-04	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	9.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	75	°C	ISO 306
Vicat Softening Temp, Rate B/120	78	°C	ISO 306
PHYSICAL	Value	Unit	Standard
Mold Shrinkage on Tensile Bar, flow (2)	1.2 - 1.4	%	SABIC Method
Density	1.18	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Melt Volume Rate, MVR at 320°C/2.16 kg	8	cm ³ /10 min	ISO 1133
ELECTRICAL	Value	Unit	Standard
Volume Resistivity	4.7E+14	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	19	kV/mm	IEC 60243-1
Relative Permittivity, 100 Hz	3	-	IEC 60250
Dissipation Factor, 100 Hz	0.0091	-	IEC 60250
Comparative Tracking Index	175	V	IEC 60112
Comparative Tracking Index, M	100	V	IEC 60112
FLAME CHARACTERISTICS	Value	Unit	Standard
UL Compliant, 94V-1 Flame Class Rating (3)(4)	1.6	mm	UL 94 by GE
Glow Wire Flammability Index 960°C, passes at	3.2	mm	IEC 60695-2-12
Oxygen Index (LOI)	48	%	ISO 4589

Source GMD, last updated:03/26/1996

Processing

Parameter	Value	Unit
Profile Extrusion		
Drying Temperature	105 - 110	°C
Drying Time	5 - 7	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	285 - 320	°C
Barrel - Zone 1 Temperature	280 - 290	°C
Barrel - Zone 2 Temperature	300 - 310	°C
Barrel - Zone 3 Temperature	310 - 320	°C
Barrel - Zone 4 Temperature	310 - 325	°C
Hopper Temperature	60 - 100	°C
Adapter Temperature	315 - 325	°C
Die Temperature	300 - 320	°C
Calibrator Temperature	60 - 80	°C

Source GMD, last updated:03/26/1996

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

Disclaimer : All information, recommendation or advice given by SABIC Innovative Plastics, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC Innovative Plastics Company, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC Innovative Plastics Company, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

* Ultem is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company.All rights reserved