

# CYCOLOY™ XCY620S resin

Tuesday, July 09, 2013

## General Information

### Product Description

PC+ ABS Automotive applications

### General

Material Status	• Commercial: Active
Availability	• North America
Uses	• Automotive Applications
Processing Method	• Injection Molding

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14		ASTM D792
Density	1.14	g/cm <sup>3</sup>	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
260°C/5.0 kg	1.22	in <sup>3</sup> /10min	
265°C/5.0 kg	1.53	in <sup>3</sup> /10min	
Molding Shrinkage - Flow (0.126 in)	0.0050 to 0.0070	in/in	Internal Method
Molding Shrinkage - Across Flow (0.126 in)	0.0050 to 0.0070	in/in	Internal Method
Water Absorption (73°F, 24 hr)	0.30	%	ISO 62
Water Absorption (Saturation, 73°F)	0.40	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.13	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	319000	psi	ISO 527-2/1
Tensile Stress (Yield)	7830	psi	ISO 527-2/50
Tensile Stress (Break)	8120	psi	ISO 527-2/50
Tensile Strain (Yield)	4.5	%	ISO 527-2/50
Tensile Strain (Break)	100	%	ISO 527-2/50
Flexural Modulus <sup>2</sup> (1.97 in Span)	334000	psi	ASTM D790
Flexural Modulus <sup>3</sup>	319000	psi	ISO 178
Flexural Strength <sup>3, 4</sup>	11900	psi	ISO 178
Flexural Strength <sup>2</sup> (Yield, 1.97 in Span)	12500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>5</sup>			ISO 179/1eA
-22°F	21	ft-lb/in <sup>2</sup>	
73°F	29	ft-lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength <sup>6</sup> (73°F)	No Break		ISO 179/1eU

**Disclaimer :** THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

\* CYCOLOY is a trademark of SABIC Innovative Plastics IPV

© 1997-2013 SABIC Innovative Plastics Holding BV. All rights reserved

# CYCOLOY™ XCY620S resin

## SABIC Innovative Plastics - Acrylonitrile Butadiene Styrene + PC

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength <sup>7</sup>			ISO 180/1A
-22°F	19	ft·lb/in <sup>2</sup>	
73°F	26	ft·lb/in <sup>2</sup>	
Instrumented Dart Impact			ASTM D3763
-22°F, Total Energy	575	in·lb	
73°F, Total Energy	487	in·lb	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi, Unannealed, 0.126 in	262	°F	
Heat Deflection Temperature <sup>8</sup>			ISO 75-2/Bf
66 psi, Unannealed, 2.52 in Span	259	°F	
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.126 in	226	°F	
Heat Deflection Temperature <sup>8</sup>			ISO 75-2/Af
264 psi, Unannealed, 2.52 in Span	223	°F	
Vicat Softening Temperature	264	°F	ASTM D1525 <sup>9</sup>
Vicat Softening Temperature	266	°F	ISO 306/B120
Ball Pressure Test			IEC 60695-10-2
167°F	Pass		
212°F <sup>10</sup>	Pass		
CLTE - Flow (-40 to 104°F)	0.000039	in/in/°F	ASTM E831
CLTE - Transverse (-40 to 104°F)	0.000039	in/in/°F	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+16	ohm	IEC 60093
Volume Resistivity	> 1.0E+16	ohm·cm	IEC 60093
Electric Strength			IEC 60243-1
0.0315 in, in Oil	990	V/mil	
0.0630 in, in Oil	640	V/mil	
0.126 in, in Oil	430	V/mil	

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	203 to 221	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Hopper Temperature	140 to 176	°F
Rear Temperature	446 to 500	°F
Middle Temperature	482 to 554	°F
Front Temperature	482 to 554	°F
Nozzle Temperature	464 to 536	°F
Processing (Melt) Temp	500 to 554	°F
Mold Temperature	140 to 194	°F

**Disclaimer :** THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

\* CYCOLOY is a trademark of SABIC Innovative Plastics IPV

© 1997-2013 SABIC Innovative Plastics Holding BV. All rights reserved

# CYCOLOY™ XCY620S resin

## SABIC Innovative Plastics - Acrylonitrile Butadiene Styrene + PC

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.051 in/min

<sup>3</sup> 0.079 in/min

<sup>4</sup> Yield

<sup>5</sup> 80\*10\*4 sp=62mm

<sup>6</sup> 80\*10\*3 sp=62mm

<sup>7</sup> 80\*10\*4

<sup>8</sup> 80\*10\*4 mm

<sup>9</sup> Rate B (120°C/h), Loading 2 (50 N)

<sup>10</sup> Approximate maximum

**Disclaimer** : THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of SABIC Holding Europe BV

\* CYCOLOY is a trademark of SABIC Innovative Plastics IPV

© 1997-2013 SABIC Innovative Plastics Holding BV. All rights reserved